




FACES	Peeled Gurjan Veneer Faces
INNER LAYERS	100% Premium Hardwood
GLUE	Melamine Urea Formaldehyde (MUF)

RECOMMENDED APPLICATIONS



Indoor Joinery



Indoor Furniture



PRODUCT DESCRIPTION

Suntree Solid MR Grade Plywood is moisture resistant interior grade plywood made from high quality hardwood veneers and is bonded with superior grade Melamine Urea Formaldehyde (MUF) resin. This gives our plywood strong enough to resist warm water up to 8 hours and can be used in hot and humid climatic conditions. This grade of plywood are mainly used for paneling, interior partitions and furnishing. This category plywood comes with 5 Years Warranty*

THICKNESS	6 MM	9 MM	12 MM	16 MM	19 MM	25 MM
NO. OF PLYS	5 PLY	7 PLY	9 PLY	11 PLY	13 PLY	17 PLY

SUNTREE SOLID MR (IS:303)

TEST ANALYSIS REPORT (As Per IS:710-2010)

TYPES OF TESTS	REFERENCE VALUE	OBSERVED VALUE
Surface	AA/AB/BB	AA
Resistance to water 3 cycle each cycle consisting of 3hrs at 60±2°C. in water and drying 8 hrs at 65±2°C	Pass Standard	Confirmed
Modulus of Elasticity Parallel to Face Grain(Avg) Across the Face Grain (Avg)	4000N/Sq.mm 5330N/Sq.mm	5330N/Sq mm 4210N/Sq.mm
Modulus of Rupture Parallel to Face Grain (Avg) Across the Face Grain Avg)	30 N/Sq.mm 15 N/Sq.mm	45 N/Sq.mm 30 N/Sq.mm

Mycological Test	Pass Standard	Confirmed
Moisture Content	Not less than 5% Not more than 15%	10%



SUNTREE[®]

Builds Confidence

 **Suntree Woods Pvt. Ltd.,**

62/ 2592, 2nd Floor, Saj Mahal Building, Madakkappillil Lane, Chittoor Road,
Near South Railway Station, Ernakulam Dist., Kerala- 682 016

 **1800 1211 791** (Toll free), +91 9778 920 958

 Email: info@suntree.co.in  www.suntree.co.in

